

EU.P.S. FOREST

Description: asphalt shingle with colored basalt.

GENERAL INFORMATION

Bituminous Compound	-		APP Modified Bitumen	
Length	EN 544	mm	1000	± 3
Width	EN 544	mm	340	± 3
Thickness	-	mm	3	± 10%
Exposed Area	-	mm	145	-
Adhesion System	-		Self-adhesive Surface	

PHYSICAL-CHEMICAL PROPERTIES

Weight	-	kg/m ²	9,8	± 8%
Mass of Fiberglass Mat	-	g/m ²	100	± 10%
Granules per Single Layer	EN 544	g/m ²	>1400	-
Bitumen per Single Layer	EN 544	g/m ²	>1300	-
Tensile Strength MD/CMD	EN 544	N/5cm	>700/>450	-
Nail Shank Tear Resistance	EN 544	N	>100	-
Granules Adhesion	EN 544	-g	<1,5	-

PACKAGING

Type		Polyethylene
Shingles per Bundle		24
m ² /bundle		3,50
Bundles/Pallet		48
m ² /pallet		168

The technical data sheet may be updated by the manufacturer without notice.

TEGOLA



OOO Tegola Roofing Products
Ul. Zavodskaya, Corpus 4
Davydovo - Orekhovo Zuyev Region,
142641 Moscow Oblast' - Russian Federation

Rev.01-02/10/19 XXXXXXXXXXXXX